




COMMERCIAL DATA SHEET

MEPJARDIN 3000 AR SPP



0958

MEPLE S.A, Z.I du Moulin,
76410 TOURVILLE LA RIVIERE

06

0958 – CPD – DK024/1

EN 13707 (2005) / EN 13969 (2005)

Sheet comprising polyester, SBS elastomer modified bitumen, heat-weldable plastic film, self-protection with slate flakes, minimum dimensions 7.92 m x 0.99 m x 3 mm, laid by torch welding.

Second layer of a weldable two-layer system for garden terrace roofs, planted terrace roofs or damp-proofing of below-grade walls.

Second layer of a weldable two-layer system for multi-purpose covering.

Resistance to external fire: PND

Reaction to fire: F

Tensile strength: longitudinal 700 ± 100 N/50 mm, transverse 600 ± 100 N/50 mm

Elongation: longitudinal $36 \pm 6\%$, transverse $42 \pm 6\%$

Resistance to static punching: L20

Impact strength : ≥ 1500 mm (méthode B)

Resistance to tearing (L/T): 230 ± 80 N

Cold pliability: $\leq -15^\circ\text{C}$

Watertightness: conforms

Root resistance: pending

05/09